



SELECTION & SPECIFICATION DATA

Type	Modified Alkyd Enamel
Description	Blackhawk 7500 Chassis Coating is designed for factory-finishing of metal material handling, agricultural and construction equipment and truck/trailer frames. This enamel produces typical alkyd-type physical properties without the common slow cure rates of most oxidizing alkyd coatings.
Features	<ul style="list-style-type: none"> • Single-component • Aggressive bond in cooler temperatures • Excellent abrasion and impact resistance • Good color retention • Fast-drying • Lead- and chromate-free
Color	Black
Primer	Self-priming on most substrates
Finish	80' 60' meter
Solids Content	52% by weight 46% by volume
Theoretical Coverage Rate	730 square feet per gallon at 1 mil DFT
VOC	<420 g/L (3.5 lbs/gal)

SUBSTRATES & SURFACE PREPARATION

Substrates	<ul style="list-style-type: none"> • Clean, bare carbon steel • Phosphated/pre-treated metals • Primed metals • Wood
All	Surfaces must be clean, dry and free of debris and loose scale. Remove dirt, dust, oil, and other contaminants.
Previously Painted Surfaces	Consult ErgonArmor

MIXING & THINNING

Mixing	May need slight agitation beyond 3 months of storage.
Thinning	Up to 10% xylene

APPLICATION EQUIPMENT

Airless Spray	Pump Size - 15:1 or greater Tip Size - 0.027 in orifice tip size is recommended Hose L/D - 200 ft (max) x 3/8 in diameter Whip L/D - 6 ft (max) x 1/4 in diameter
----------------------	--

CLEANUP & SAFETY

Cleanup	Xylene or similar solvent
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

PACKAGING, HANDLING & STORAGE

Shelf Life	12 months at 75°F (24°C) When kept at recommended storage conditions and in original unopened containers.
Storage Conditions	40°F – 110°F (4°C – 43°C) 0 – 100% relative humidity
Package Sizes & Shipping Weights	55 gallon drum - 510 lbs (231 kg)

CURE SCHEDULE & RECOAT WINDOW

Dry to Touch, 77°F (25°C)	30 minutes
Tack Free, 77°F (25°C)	90 minutes
Dry Hard, 77°F (25°C)	24 hours

PERFORMANCE DATA

SPECIFICATIONS	DETAILS	RESULTS
Early Water Resistance ASTM D714-02	4 hour cure	10 - No blistering
1 Week Adhesion Test ASTM D3359	CRS, Aluminum	2B
Hardness Development ASTM D4366	1 week cure	72 osc
Taber Abrasion ASTM D1044	1 week cure (CS-10, 826 cycles)	0.2197 g average loss 2.7 mils average
Impact Resistance ASTM G14	1 week cure	Direct: 35 lbs Reverse: 5 lbs
Salt Spray Resistance ASTM B117	4 DFT	500+ hours

Rev 03/19

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.

