

SELECTION & SPECIFICATION DATA

Generic Type	Asphalt Cutback
Description	Blackhawk Liquid Asphalt Coating is a liquefied asphalt damp proofing compound formulated to be easily applied by roller brush or spray equipment. Blackhawk Liquid Asphalt Coating can be used as a primer on surfaces to receive Blackhawk Pipe Joint Mastic, Hawk-Seal, and Hawk-Wrap, or as a coating. It dries to a tough, durable, and water-detering layer that maintains excellent performance over a wide range of temperatures and conditions. Available in winter and summer grades.
Recommended Uses	Coating for: <ul style="list-style-type: none"> • Precast concrete manholes • Electrical boxes • Burial vaults • Septic tanks • Box culverts • Pipes
Color	Black
Topcoats	Consult ErgonArmor
Finish	Matte
Dry Film Thickness	5 – 20 mils
Solids Content	By Weight 65% +/- 5%
Theoretical Coverage Rate	160 sq ft per gallon at 10 wet mils
VOC Value(s)	<350 g/L

SUBSTRATES & SURFACE PREPARATION

General	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
Mixing	No mixing necessary
Thinning	DO NOT THIN
Spray Application	Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.
Airless Spray	Pump Size 15:1 or greater

Hose Length/ Diameter	200 ft x ½"
Whip Length/ Diameter	15 ft x ¼"
Brush	Apply with a wide fiber brush in order to create a smooth uniform film.
Roller	Use a low nap phenolic core roller.

CLEANUP & SAFETY

Cleanup	Use mineral spirits for suitable cleanup. In case of spillage, absorb and dispose of in accordance with local applicable regulations. Refer to SDS for more information.
Safety	Read and follow all caution statements on this product data sheet and on the SDS for this product. Wear protective clothing, gloves and eye protection.

PACKAGING, HANDLING & STORAGE

Ventilation	Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.
Shelf Life	12 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
Shipping Weight	Pails 40 lbs Drums 445 lbs
Storage Temperature & Humidity	40° – 110°F (4° – 43°C) 0 – 100% Relative Humidity
Storage	Store Indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F, for a duration of no more than 14-days. Always inspect the product prior to use.
Sizing and Specifications	5 gallon (4.7 net fill) 55 gallon (53 net fill)

Rev 02/17

SAFETY

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and material safety data sheets before using. While all statements, technical information, and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. Please contact ErgonArmor for further information at 877-982-7667 or FAX 601-933-3381. For all Terms and Conditions of Sale see ergonarmor.com.

ORDERING INFORMATION

For additional information, prices, or to place an order, please contact your ErgonArmor sales representative. If you do not know the name of your sales representative, call 877-98ARMOR.